

Garnet



Garnet

Chemical Analysis	
Copper (as CuO)	Less than 0.01% m/n
Lead (as PbO)	Less than 0.01% m/n
Nickel (as NiO)	0.08% m/n
Zinc (as ZnO)	0.02% m/n
Total Iron (as FeO)	28.4% m/n
Water - soluble Chlorine (as Cl)	Less than 0.001% m/n

Standard Size	Approximate Size	Average Anchor Pattern	Normal Application
G 1030	500 μ m - 1.70 mm	$\pm$ 130 μ m	Suitable for blasting on stainless steel, aluminium & normal steel
G 2040	425 μ m - 850 μ m	$\pm$ 70 μ m	Water filtration
G 3060	250 μ m - 600 μ m	$\pm$ 30 μ m	Water jet cutting

Anchor pattern is affected by other factors other than the abrasive, e.g. nozzle - surface distance, work surface hardness & degree of rusting, etc.

21/62 หมู่ 3 ต.ลำโพ อ.บางบัวทอง จ.นนทบุรี 11110
21/62 Moo 3 Lampo, Bangbuathong, Nonthaburi, 11110
Tel : (+66) 2 194-4346-7 Fax : (+66) 2194-4348
E - Mail : sales@rpv.co.th
www.rpv.co.th